

# COLORSTEP® 0 VIOLET B4119

颜料索引: Pigment Violet 19

C.I.No: 73900

化学名称: 喹吡啶酮紫

CAS No. 1047-16-1

## 理化数据

筛余 (120mesh)	≤5.0
吸油量(ml/100g)	45-55
PH 值 (at g/l .C)	7-8
水溶物 (@ 20°C)	≤1.5
水份(%)	≤1.5

## 牢度性能

耐迁移	5
耐光 - (全色)	8
耐光 - SD 1/3 (Reduction)	8
耐温 - (全色)[°C]	270
耐温 - SD 1/3 (Reduction) [°C]	270

## 产品描述

是红光紫色粉末，具有优异的耐光和耐热稳定性；主要用于高档工业涂料，与无机颜料如氧化铁红、钼红等拼色，透明型可用于金属装饰漆；亦可用于塑料着色，在聚丙烯中可承受 300°C。可与颜料红 122 拼出接近标准品红色调，用于层压塑料薄膜及 PP 原浆着色等。

## 应用领域

一般工业漆	推荐
卷材涂料	推荐
粉末涂料	推荐
PO	推荐
PVC & 橡胶	推荐
工程塑料	推荐
油墨	推荐

## 化学性能

耐酸	5
耐碱	5
耐乙醇	5
耐酯	5
耐苯	5
耐酮	5
耐皂洗	5

## 化学品名录状况

COLORSTEP® 0 VIOLET B4119 所有成分 在下列国家化学品名录中列明

AICS (澳大利亚)、DSL (加拿大)、ECL (韩国)、EINECS [欧洲]、IECSC [中国]、MITI [日本]、NZIOC (新西兰)、PICCS (菲律宾)

TSCA [美国]

**NOTICE:** All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.