

COLORSTEP® 0 VIOLET B4023

颜料索引: Pigment Violet 23

C.I.No: 51319

化学名称: 吡啶紫

CAS No. 6358-30-1

理化数据

筛余 (120mesh)	≤5.0
吸油量(ml/100g)	40-50
PH 值 (at g/l .C)	5-6
水溶物 (@ 20°C)	≤1.5
水份(%)	≤1.5

牢度性能

耐迁移	5
耐光 - (全色)	8
耐光 - SD 1/3 (Reduction)	8
耐温 - (全色)[°C]	250
耐温 - SD 1/3 (Reduction) [°C]	250

产品描述

是蓝光紫色粉末，具有全面应用牢固，不寻常的高着色强度。广泛用于涂料、油墨、塑料与织物印染等领域，在涂料着色时耐罩光漆牢度好，可用于空气自干漆、汽车涂料及烘烤漆，尤其是做对 CuPc 调色剂、获得强红光色调的乳胶漆；用于塑料着色，聚烯烃中耐热 280°C，高着色力，也用于聚酯及 PE 的原浆着色；良好的耐光耐气候牢度使其适用于涂料印花及印刷油墨。

应用领域

一般工业漆	推荐
卷材涂料	推荐
粉末涂料	推荐
PO	推荐
PVC & 橡胶	推荐
工程塑料	推荐
油墨	推荐

化学性能

耐酸	5
耐碱	5
耐乙醇	5
耐酯	5
耐苯	5
耐酮	5
耐皂洗	5

化学品名录状况

COLORSTEP® 0 VIOLET B4023 所有成分 在下列国家化学品名录中列明

AICS (澳大利亚)、DSL (加拿大)、ECL (韩国)、EINECS [欧洲]、IECSC [中国]、MITI [日本]、NZIOC (新西兰)、PICCS (菲律宾)

TSCA [美国]

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.